

TEST RESULTS

TS EN 13823+A1	FIGRA _{0,2} ≤ 120 W/s	3	33,02	(-)
	FIGRA _{0,4}		28,76	(-)
	SMOGR _A ≤ 30 m ² /s ²		3,44	(-)
	TSP _{600s} ≤ 50 m ²		42,41	(-)

Classification and direct application area

Classification reference

4.2. Sınıflandırma

The class of the acoustic felt product determined based on its behavior in the event of a fire

B

The class of the acoustic felt product determined based on its behavior in the event of a fire

s1

The class of the acoustic felt product determined based on its behavior in the event of a fire

d0

Fire Behavior	Smoke Formation	Flaming Droplets
B	s1	d0
FIRE REACTION CLASS : B-s1,d0		

Scope of Application

This classification applies to products manufactured with the same formulation, of the same type, and bearing the same name, as detailed in Article 2, within the following final applications.

